



TEST REPORT

Sample As Received	Reference: General	Last Revised: 15/07/2015
Report No: 150708(i)		Order #: -
Date Received: 6/07/2015		Date Completed: 8/07/2015
Client: CLEAR FOCUS ONE WAY VISION PTY LTD		Telephone: +61 7 5504 5512
Address: P.O. Box 173, Chevron Island QLD 4217		Submitted: Brent Shire

This test report supersedes report numbered 150708

Test Description	Method
Assessment	VL - Assessment

Thermal Requirements

ADDITIONAL TESTING

Sample Description: White synthetic perforated self-adhesive sheet material (Clear Focus One Way Vision PromoVue), Adhered to 3.0mm Plain Glass

Method	Description	Requirement	Result
ISO 15025	Face Ignition	The following requirements shall be met:	
		a) No specimen shall give hole formation	No Holes
		b) No specimen shall give molten or flaming debris	No Debris
		c) The mean value of the after flame shall be $\leq 2s$	No Afterflame
		d) The mean value of the afterglow shall be $\leq 2s$	No Afterglow
Observations		Specimen has achieved desired results.	
ISO 17493	Heat Resistance 200 Deg C	Material Shall:	
		Not Melt	No melting
		Not Drip	No dripping
		Not Ignite	No ignition
		Not shrink more than 10% (Length)	0%
		Not shrink more than 10% (Width)	0%
Observations		Specimen has achieved desired results. However, edges curled.	



NATA Accredited Laboratory  
Number: 14722

This document is issued in accordance with NATA accreditation requirements.

Accredited for compliance with ISO/IEC 17025

The results of the tests, calibrations and/or measurements in this document are traceable to Australian National Standards.

This document shall not be reproduced except in full

**AUTHORISED SIGNATORY:**

Legend:

NA = Not Applicable

NT = Not Tested

NS = Not Supplied

TBA = To Be Ascertained

